

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 : C08L 23/08, 23/06, 23/10	A1	(11) International Publication Number: WO 98/47958 (43) International Publication Date: 29 October 1998 (29.10.98)
(21) International Application Number: PCT/US98/08319 (22) International Filing Date: 21 April 1998 (21.04.98) (30) Priority Data: 97201191.0 23 April 1997 (23.04.97) EP (34) Countries for which the regional or international application was filed: AT et al. (71) Applicant (for all designated States except US): E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): GARCIA DURAN, Juan Antonio [ES/CH]; 26, avenue de l'Amandolier, CH-1208 Geneva (CH). ROLLAND, Loic, Pierre [FR/FR]; Résidence Metna, 234, avenue de la Grande Champagne, F-01220 Divonne-les-Bains (FR). (74) Agent: KELLY, Patricia, L.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		(81) Designated States: AU, BR, CA, CZ, JP, KR, SG, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: FLEXIBLE THERMOPLASTIC POLYOLEFIN COMPOSITIONS (57) Abstract Halogen-free thermoplastic blends of a polar rubber, ethylene vinyl acetate and a polyolefin are provided which are flexible and are particularly useful in replacing polyvinyl chloride for production of various products.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Title

Flexible Thermoplastic Polyolefin Compositions

5

Background of the Invention

Field of Invention:

10 This invention relates to polyolefin compositions and more particularly to such compositions which are flexible and to shaped articles made from them.

Background Discussion:

15 Polyvinyl chloride (PVC) products have been on the market for many years and are commonly used in a large variety of applications. With the trend toward a chlorine-free environment, there is in some market segments such as construction, automotive and wires and cables industries a need for an alternative to PVC. Ethylene-propylene-diamine-methylene (EPDM) rubbers are alternatives, but tend to be costly.

20 WO 93/19118 and WO 89/06256 disclose PVC-free compositions that are suitable for use as coatings for electrical cables. These compositions contain several components that are similar to those described, but lack, i.a., the terpolymer described in the present application.

25 EP 0 703 271 A1 discloses flexible, halogen-free thermoplastic polyolefin compositions, including certain which are based upon ethylene vinyl acetate, ethylene vinyl acetate carbon monoxide and very low density polyethylene. While these compositions are useful in many applications, they have been found to soften or melt unacceptably under certain high temperature applications.

30

Summary of the Invention

According to the present invention there is provided a flexible, halogen-free polymer composition which comprises a blend of:

35

(1) a polar rubber selected from the group consisting of (a) ethylene vinyl acetate carbon monoxide terpolymer containing 30-90% by weight ethylene, 10-70% by weight vinyl acetate and 1-20% by weight carbon monoxide, (b) acrylonitrile butadiene rubber, (c) acrylate acrylonitrile styrene rubber and (d) ethylene n-

butylacrylate carbon monoxide terpolymer containing 30-90% by weight ethylene, 10-70% by weight n-butylacrylate and 1-20% by weight carbon monoxide;

(2) ethylene vinyl acetate containing 30-90% by weight ethylene and 10-70% by weight vinyl acetate; and

(3) a polyolefin selected from the group consisting of (a) linear low density polyethylene having a specific gravity greater than 0.925, (b) low density polyethylene having a specific gravity greater than 0.920, (c) high density polyethylene, (d) polypropylene homopolymer and (e) ethylene-polypropylene copolymer.

It is to be understood that more than one type of polar rubber, ethylene vinyl acetate and/or polyolefin can be used together in the present invention.

15

Polymer blends according to the present invention have been found to have, in addition to the advantages of halogen-free blends, surprisingly high heat stability. High heat stability is an important characteristic for certain end-uses of the blends, including, in the automotive field, for sun visors, trunk covers, door panels, dashboards, and the like.

20

Detailed Description of the Invention

The present invention relates to flexible, halogen-free thermoplastic polymer blends which are useful in making sheets, coated fabrics and injection molded parts. These end-products have characteristics similar to those made from polyvinyl chloride (PVC) containing blends, and in addition, demonstrate improved flexibility at low temperatures, and are free from halogen.

25

Certain terms mentioned below are to be understood to have the meanings indicated; otherwise, terms used in this application should be attributed the meanings understood in the art.

30

Unless otherwise stated, percentage weight ranges for each of the components in the composition of the present invention are calculated exclusive of any additives which may be present.

35

The EVACO terpolymer (component (1)(a)) useful in this invention preferably contains 30-90% by weight of ethylene, 10-70% by weight of vinyl acetate and 1-20%

by weight of carbon monoxide, more preferably 55-65% by weight of ethylene and 20-30% by weight of vinyl acetate and 5-15% by weight carbon monoxide. In general, EVACO used in the present invention will have a melt flow index (MFI) in the range of 1-50 g/10 min., preferably in the range of 10-40 g/10min. as determined by ASTM D-1238 (measured at 2,16 kg and 190 °C). EVACO is well known in the art, and commercially available under the name Elvaloy® from the DuPont Company.

Acrylonitrile butadiene rubbers and acrylate acrylonitrile styrene rubbers (components (1)(b) and (1)(c)) are well known in the art. Suitable grades are available under the names CHEMIGUM and SUNIGUM from the Goodyear Tire and Rubber Company.

The EnBACO terpolymer (component (1)(d)) useful in this invention preferably contains 30-90% by weight of ethylene, 10-70% by weight of n-butylacrylate and 1-20% by weight of carbon monoxide, more preferably 55-65% by weight of ethylene and 25-35% by weight of n-butylacrylate and 5-15% by weight carbon monoxide. In general, EnBACO used in the present invention will have a melt flow index (MFI) in the range of 1-50 g/10 min., preferably in the range of 5-30 g/10min. as determined by ASTM D-1238 (measured at 2,16 kg and 190 °C). EnBACO is well known in the art, and commercially available under the name Elvaloy® from the DuPont Company.

Component (1) preferably comprises 5-65% by weight of the composition of the present invention, more preferably 10-50% by weight, still more preferably 20-40% by weight.

The EVA copolymer (component (2)) useful in this invention preferably contains 30-90% by weight of ethylene and 10-70% by weight of vinyl acetate, more preferably 55-75 % by weight of ethylene and 15-30 % by weight of vinyl acetate. In general, the EVA used in the present invention has a melt flow index (MFI) in the range of 0.05-100 g/10 min., preferably less than 50 g/10min. as determined by ASTM D-1238 (measured at 2,16 kg and 190 °C) and is commercially available under the name Elvax® from the DuPont Company.

Component (2) preferably comprises 5-65% by weight of the composition of the present invention, more preferably 20-50% by weight, still more preferably 20-30% by weight.

The LLDPE (linear low density polyethylene), LDPE (low density polyethylene), HDPE (high density polyethylene), PP (polypropylene) homopolymer and E-PP (ethylene-propylene) copolymer (component (3)) are well known in the art and

commercially available. These polyolefins can be produced through conventional polymerization processes, or through the more recently developed single-site catalyst technology. Single-site catalyst technology is described in numerous publications, including US Patent Nos. 5,272,236 and 5,278,272 and PCT Publication WO 94/06857, and is particularly suitable for the production of LLDPE.

LLDPE is used herein to mean linear low density polyethylene having a specific gravity greater than 0.925 g/cc, and includes copolymers of ethylene and other alpha-olefins such as 1-butene, 1-hexene, and 1-octene. LDPE is used herein to mean low density polyethylene having a specific gravity greater than 0.920. It is believed all available grades of HDPE, PP and E-PP copolymer can be used in the blends of the present invention.

Component (3) preferably comprises 5-65% by weight of the composition of the present invention, more preferably 10-50% by weight, still more preferably 20-40% by weight.

In addition to its polymer components, the composition of the present invention can be blended with common additives such as reinforcing and non-reinforcing fillers, flame retardant fillers such as aluminium trihydrate, antioxidants, UV stabilizers, lubricants (e.g., oleamide), antiblocking agents, antistatic agents, waxes, coupling agents for fillers, pigments, titanium dioxide, talc and other processing aids (e.g., zinc stearate) known in the polymer compounding art. These additives may comprise up to about 70 weight percent of the total composition based on polymer components plus additives (the polymer components being present in amounts with respect to each other in the proportions previously specified). The precise amount of additive to be used will depend upon the type of additive, end-use, etc.

The blends of the invention can be prepared by mixing the polymeric ingredients and optional additives by use of conventional masticating equipment, for example, a rubber mill, Brabender Mixer, Banbury Mixer, Buss-ko kneader, Farrel continuous mixer or twin screw continuous mixer. Mixing times should be sufficient to obtain homogeneous blends. Satisfactory mixing times depend upon the types of polymers and upon the type of mixing equipment used. Typically, mixing times of about 1 to 5 minutes are satisfactory. If the polymer blend is obviously non-homogeneous, additional mixing is required.

The invention can be further understood by the following examples in which percentages are by weight and temperatures are in degrees Celsius.

Examples

Legend

- 5
- MFI = melt flow index
 EVACO = ethylene vinyl acetate carbon monoxide
 NBR = acrylonitrile butadiene rubber
 ANSR = acrylate acrylonitrile styrene rubber
- 10
- EVA = ethylene vinyl acetate
 VLDPE = very low density polyethylene
 LLDPE = linear low density polyethylene
 HDPE = high density polyethylene
 LDPE = low density polyethylene
- 15
- E-PP = ethylene propylene copolymer
 PP = polypropylene homopolymer

Procedure

- 20 A blend is prepared by melt-compounding the following components in the proportions set forth in Table 1 below.
- EVACO (79.5% ethylene, 20.5% vinyl acetate and 8% carbon monoxide) having a MFI (190°/2.16 kg) of 15
 - 25 • NBR
 - ANSR having a specific gravity of 1.04 g/cc and a Mooney viscosity (ML1+4/100°) of 44
 - EVA₁ (60% ethylene and 40% vinyl acetate) having a MFI (190°/2.16 kg) of 3.0
 - EVA₂ (75% ethylene and 25% vinyl acetate) having a MFI (190°/2.16 kg) of 2.0
 - 30 • EVA₃ (82% ethylene and 18% vinyl acetate) having a MFI (190°/2.16 kg) of 0.7
 - VLDPE having a specific gravity of 0.900 and a MFI (190°/2.16 kg) of 1.0
 - LLDPE having a specific gravity of 0.930 g/cc and a MFI (190°/2.16 kg) of 1.0
 - HDPE having a specific gravity of 0.958 g/cc and a MFI (190°/2.16 kg) of 1.2
 - LDPE having a specific gravity of 0.922 g/cc and a MFI (190°/2.16 kg) of 0.85
 - 35 • E-PP having a specific gravity of 0.906 g/cc and a MFI (230°/2.16 kg) of 1.0
 - PP having a specific gravity of 0.910 g/cc and a MFI (190°/2.16 kg) of 1.5
 - UV stabilizers (blend of 50% by weight TINUVIN 622 LD (an oligomeric, sterically hindered amine stabilizer available from Ciba; and 50% by weight TINUVIN 328 (a benzotriazole type stabilizer available from Ciba))

- antioxidant - phenolic type available under the name IRGANOX 1010 from Ciba
- Zinc stearate

Melt compounding is carried out on a two roll mill with batches from 100 grams at 170-190°C for ca. 5 minutes. The milled product is formed into a testing plaque in a hydraulic press at 170-190°C for 5 minutes. Afterwards stress-strain testing (ASTM D-638) and Heat Deformation at 85, 105, 115 and 145 deg.C (a 30 gr weight is hanged to a plate sample having a thickness of 0.5 mm, a length of 10 cm and a width of 10 mm) are carried out. Results are shown in Table 1.

10

Table 1

<u>Example numbers</u>		<u>PA*</u>	<u>2</u>	<u>3</u>	<u>4</u>	<u>5</u>	<u>6</u>	<u>7</u>	<u>8</u>
15	EVACO	30	30	30	30	30	30	-	-
	NBR	-	-	-	-	-	-	30	-
	ANSR	-	-	-	-	-	-	-	30
	EVA1	4.9	4.9	4.9	4.9	4.9	4.9	4.9	4.9
	EVA2	16	16	16	16	16	16	16	16
20	EVA3	16	16	16	16	16	16	16	16
	VLDPE	30	-	-	-	-	-	30	30
	LLDPE	-	30	-	-	-	-	-	-
	HDPE	-	-	30	-	-	-	-	-
	LDPE	-	-	-	30	-	-	-	-
25	E-PP	-	-	-	-	30	-	-	-
	PP	-	-	-	-	-	30	-	-
	UV stabilizer	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6
	Antioxidant	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	Zinc stearate	2	2	2	2	2	2	2	2
30	Tensile strength (MPa)	20.1	24.7	16.5	16.0	15.6	9.0	10.8	11.1
	Tensile elongation (%)	764	862	719	718	839	326	580	602
	Heat def. at 85°C (%)	0	0	0	0	0	0	0	0
	Heat def. at 105°C (%)	20	20	0	0	10	0	X	X
	Heat def. at 115°C (%)	X	50	0	X	40	0	-	-
35	Heat def. at 145°C (%)	-	-	-	-	-	0	-	-

* - prior art

X - sample breaks

One can see that the formulations containing LLDPE, HDPE, E-PP or PP show particularly lower heat deformation values. For automotive products, this brings a significant benefit.

- 5 Moreover, one can see that the use of NBR or ANSR in place of EVACO give good tensile properties although their heat deformation results are below some of the other formulations.

Claims

1. A flexible, halogen-free polymer composition comprising a blend of
 - 5 (1) a polar rubber selected from the group consisting of (a) ethylene vinyl acetate carbon monoxide terpolymer containing 30-90% by weight ethylene, 10-70% by weight vinyl acetate and 1-20% by weight carbon monoxide, (b) acrylonitrile butadiene rubber, (c) acrylate acrylonitrile styrene rubber and (d) ethylene n-butylacrylate carbon monoxide
10 terpolymer containing 30-90% by weight ethylene, 10-70% by weight n-butylacrylate and 1-20% by weight carbon monoxide;
 - (2) ethylene vinyl acetate containing 30-90% by weight ethylene and 10-
15 70% by weight vinyl acetate; and
 - (3) a polyolefin selected from the group consisting of (a) linear low density polyethylene having a specific gravity greater than 0.925, (b) low
20 density polyethylene having a specific gravity greater than 0.920, (c) high density polyethylene, (d) polypropylene homopolymer and (e) ethylene-polypropylene copolymer.
2. A blend according to claim 1 wherein component (1) comprises 5-65 % by weight of the blend, component (2) comprises 5-65 % by weight of the blend, and
25 component (3) comprises 5-65 % by weight of the blend.
3. A blend according to claim 1 wherein component (1) comprises 20-50% by weight of the blend, component (2) comprises 20-50% by weight of the blend and component (3) comprises 20-50% by weight of the blend.
- 30 4. A shaped article formed from a blend according to claim 1.

INTERNATIONAL SEARCH REPORT

national Application No
PCT/US 98/08319

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08L23/08 C08L23/06 C08L23/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0 703 271 A (DU PONT INT) 27 March 1996 see claims	1-4
Y	----- DATABASE WPI Section Ch, Week 8638 Derwent Publications Ltd., London, GB; Class A17, AN 86-248784 XP002043154 & JP 61 176 637 A (SEKISUI CHEM IND CO LTD) , 8 August 1986 see abstract	1-4
A	----- WO 94 04610 A (DU PONT ; SPELTHANN HEINZ H (CH)) 3 March 1994 see page 4, line 11; examples	1-4



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
 "E" earlier document but published on or after the international filing date
 "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
 "O" document referring to an oral disclosure, use, exhibition or other means
 "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
 "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
 "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
 "&" document member of the same patent family

Date of the actual completion of the international search

3 August 1998

Date of mailing of the international search report

12/08/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-2018

Authorized officer

Clemente Garcia, R

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/08319

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0703271 A	27-03-1996	CA 2200183 A	28-03-1996
		EP 0782590 A	09-07-1997
		JP 10506139 T	16-06-1998
		NO 971308 A	20-03-1997
		WO 9609331 A	28-03-1996
WO 9404610 A	03-03-1994	CA 2142454 A	03-03-1994
		DE 69310747 D	19-06-1997
		DE 69310747 T	18-12-1997
		EP 0655079 A	31-05-1995
		JP 8500149 T	09-01-1996
		MX 9304937 A	31-08-1994
		US 5610234 A	11-03-1997